



# Quantity Estimate Sheet

## Protal Liquid Pipeline Coatings

Weld Joints	
Pipe Diameter	Welds per Liter
4"	9
6"	6
8"	4.5
10"	3.6
12"	3
16"	2.25
20"	1.8
24"	1.5
30"	1.2
36"	1
42"	0.86
48"	0.75

**Note:** Estimates are based on field experience on weld joints with 2" to 3" cut-back and applied at 20 to 30 mils average. Actual coverage may vary depending on cut-back and mil thickness.

Pipe ( <i>Hand Applied</i> )		
Thickness in mils	Theoretical Coverage per Liter	Actual Coverage per Liter
25 mils	17 ft <sup>2</sup>	12 ft <sup>2</sup>
30 mils	14 ft <sup>2</sup>	10 ft <sup>2</sup>
35 mils	12 ft <sup>2</sup>	8.5 ft <sup>2</sup>

Pipe ( <i>Spray Applied</i> )	
Thickness in mils	Theoretical Coverage per Liter
20 mils	21 ft <sup>2</sup>
25 mils	17 ft <sup>2</sup>
30 mils	14 ft <sup>2</sup>
35 mils	12 ft <sup>2</sup>

**Note:** Actual coverage to be determined by applicator.



**DENSO NORTH AMERICA INC.**

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 416-291-3435  
Fax: 416-291-0898

**HOUSTON:**  
18211 Chisholm Trail,  
Houston, Texas,  
U.S.A. 77060  
Tel: 281-821-3355  
Fax: 281-821-0304

[www.densona.com](http://www.densona.com)

*A Member of Winn & Coales International*